

**EFFECT OF SILANE
E-GLASS/POLYESTER**

TREATMENT	STRENGTH*	
	DRY	WET**
NO SILANE	100	26
VINYL SILANE	81	31
GLYCIDYL SILANE	108	41
METHACRYL SILANE	120	79

***AS % OF DRY STRENGTH WITH NO SILANE**

****72 HOUR WATER BOIL.....THE TEST**

FIBER TREATMENT STEPS

- Spread
- Clean
- Etch
- Coat
- Dry
- Cure